


FLATWISE PLANE SHEAR FATIGUE FIXTURE (SS) WITH THREE SETS OF BONDING PLATES (AL) (COMPRESSION MODE)



Specimen:	Width	Any width up to 3"
	Thickness	0.25" to 0.75" (optional plates for thicker samples)
	Length	Up to 9"
Fixture:	Construction	Stainless steel with aluminum bonding plates
	Temperature	-120 to 250°F (-85 to 122°C)
	Mounting	1"-14 threaded studs to locking nuts
	Capacity	20,000 lbs (88.9 kN)
	Weight	20 lbs approximately
	Dimensions	Assembled 3" x 2.5" x 14.5"
	Bonding	Supplied with 3 sets of aluminum bonding plates
	Standard	Manufactured in accordance with ASTM C273 and C394

Model No. ASTM.C0394.11 - Sandwich Flatwise Plane Shear Fixture (Compression Mode) - Specimen configuration up to 9" long and 3" wide. Constructed from stainless steel except for the three sets of loading plates, which are constructed from aluminum with a protective black anodized coating. The fixture includes an upper and lower loading anvil with a groove to accept loading plates. Supplied with 1" -14 threaded studs and locking nuts. Capacity: 20,000 lbs (88.9 kN) -120 to 250°F (-85 to 122°C). Fixture is constructed in accordance with ASTM C394.

MODEL NO. ASTM.C0394.11

ASTM, EDGEWISE, COMPRESSION, SHEAR,

ACCESSORIES

Model No. ACC.C0394.1101 - Set of (2) Additional aluminum bonding plates 9" long by 3" wide
Model No. ACC.C0394.1102 - Set of (2) Additional high strength steel bonding plates 9" x 3" wide
Model No. ACC.C0394.1103 - Set of (2) Additional stainless steel bonding plates 9" long by 3" wide
Model No. ACC.C0394.1104 - Set of (2) Customer specified material
Model No. ACC.C0394.1105 - Extensometer Bracket

SPARE PARTS

Please contact us for spare or replacement parts

REFERENCE DOCUMENT AND TEST METHOD SCOPE:

SCOPE: <http://www.astm.org/Standards/C394.htm>
ASTM C394/C394M-13

Standard Test Method for Shear Fatigue of Sandwich Core Materials

1.1 This test method determines the effect of repeated shear forces on core material used in sandwich panels. Permissible core material forms include those with continuous bonding surfaces (such as balsa wood and foams) as well as those with discontinuous bonding surfaces (such as honeycomb).

1.2 This test method is limited to test specimens subjected to constant amplitude uniaxial loading, where the machine is controlled so that the test specimen is subjected to repetitive constant amplitude force (stress) cycles. Either shear stress or applied force may be used as a constant amplitude fatigue variable.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard. Within the text, the inch-pound units are shown in brackets.

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

Extracted, with permission, from ASTM C394 Standard Test Method for Shear Fatigue of Sandwich Core Materials, copyright ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428. A copy of the complete standard may be purchased from ASTM International, www.astm.org