



1" WIDE, 6" SPAN, FULLY ARTICULATING THREE & FOUR POINT FLEXURE FIXTURE WITH 4.5mm DIAMETER LOADING PINS (SS)



Specimen:	Width	Any width up to 1"
	Thickness	Any thickness up to 1/2"
	Length	Any length
Fixture:	Support Spans	Any span from 1/2" to 6"
	Supports	Articulating with 4.5mm cylindrical supports
	Construction	Stainless steel
	Temperature	-240 to 600°F (-152 to 318°C)
	Mounting	12mm male clevis top, 1/2"-20 coupling bottom
	Capacity	1,000 lbs (4.4 kN)
	Weight	10 lbs approximately
	Dimensions	Assembled - 8" x 2" x 8"
Standard	Manufactured in accordance with ASTM C1161	

Model No. ASTM.C1161.10 Fully Articulating Three & Four Point Flexure Fixture

Specimen support spans adjustable to 6" and four point loading span adjustable to 3". The rolling and pivoting specimen loading pins are 4.5mm in diameter and accommodate specimens up to 1" wide. Capacity: 1,000 lbs (4.4 kN) at temperature ranges up to 600°F. Constructed from stainless steel in accordance with ASTM C1161.

Specimen supports: Incorporate free rolling loading pins of 4.5mm diameter. One of the 1.5" tall supports is free to pivot as much as 7° in either direction to provide complete seating and maximum specimen contact.

Lower Support Base: The support span is measured along a center finding scale located on the front surface of the 7" support base. The base may be used on a compression platen or mounted with the 1/2"-20 threaded coupling.

3 & 4 Point Loading Head: The support span is measured along a center finding scale located on the the front surface of the loading head. The head is pivoted and may be allowed to float freely or can be locked rigid with a locking nut. The loading head is supplied with 12mm (Type "O") male clevis type adapter with 6mm diameter dowel pin hole. (Dowel pin not included.)

MODEL NO. ASTM.C1161.10

ASTM, CERAMIC, FLEX, COMPRESSION

ACCESSORIES

ACC.C1161.1001 - Extra Set of (4) 1/4" Diameter Loading Pins
ACC.C1161.1002 - Extra Set of (4) Rockers and 1 Fixed Support for 1/4" Pins
ACC.C1161.1003 - Extra Set of (4) 2.5mm Diameter Loading Pins
ACC.C1161.1004 - Extra Set of (4) Rockers and 1 Fixed Support for 2.5mm Pins
ACC.C1161.1005 - Extra Set of (4) 9mm Diameter Loading Pins
ACC.C1161.1006 - Extra Set of (4) Rockers and 1 Fixed Support for 9mm Pins
ACC.C1161.1007 - 1.25" Male Clevis for 4 Point Loading Head
ACC.C1161.1008 - 5/8" Male Clevis for 4 Point Loading Head
ACC.C1161.1009 - 1/2" Male Clevis for 4 Point Loading Head

Lower fixture attachment is supplied with 1/2" -20 female coupling (Common adapter sizes include:)

Model No. M01S21 - 1/2" Male Clevis (Type B) to 1/2" -20 Threaded Stud
Model No. M02S21 - 5/8" Male Clevis (Type C) to 1/2" -20 Threaded Stud
Model No. M03S21 - 1.25" Male Clevis (Type D) to 1/2" -20 Threaded Stud
Model No. M12S21 - 12mm Male Clevis (Type O) to 1/2" -20 Threaded Stud
Model No. S36S21 - 1" -14 to 1/2" -20 Threaded Step Stud
Model No. LN21 - 1/2" -20 Threaded Locking Nut with Knurled OD

SPARE PARTS

SPA.C1161.1001 - Extra Set of (4) 4.5mm Diameter Loading Pins
SPA.C1161.1002 - Extra Set of (4) Rockers and 1 Fixed Support for 4.5mm Pins
SPA.C1161.1003 - Extra Set of (2) Anvil/Rocker/Roller Assemblies

REFERENCE DOCUMENT AND TEST METHOD SCOPE:

<http://www.astm.org/Standards/C1161.htm>

ASTM C1161-13

Standard Test Method for Flexural Strength of Advanced Ceramics at Ambient Temperature

1.1 This test method covers the determination of flexural strength of advanced ceramic materials at ambient temperature. Four-point–1/4 point and three-point loadings with prescribed spans are the standard as shown in Fig. 1. Rectangular specimens of prescribed cross-section sizes are used with specified features in prescribed specimen-fixture combinations. Test specimens may be 3 by 4 by 45 to 50 mm in size that are tested on 40 mm outer span four-point or three-point fixtures. Alternatively, test specimens and fixture spans half or twice these sizes may be used. The method permits testing of machined or as-fired test specimens. Several options for machining preparation are included: application matched machining, customary procedure, or a specified standard procedure. This method describes the apparatus, specimen requirements, test procedure, calculations, and reporting requirements. The test method is applicable to monolithic or particulate- or whisker-reinforced ceramics. It may also be used for glasses. It is not applicable to continuous fiber-reinforced ceramic composites.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

Extracted, with permission, from ASTM C1161 Standard Test Method for Flexural Strength of Advanced Ceramics at Ambient Temperature, copyright ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428. A copy of the complete standard may be purchased from ASTM International, www.astm.org